

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 025 985 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
09.08.2000 Bulletin 2000/32

(51) Int. Cl.⁷: B31F 1/20

(21) Application number: 00200107.1

(22) Date of filing: 13.01.2000

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: Gigola, Antonio
I-25046 Cazzago San Martino (Brescia) (IT)

(74) Representative:
Faraggiana, Vittorio, Dr. Ing.
Ingg. Guzzi & Ravizza S.r.l.
Via Vincenzo Monti 8
20123 Milano (IT)

(30) Priority: 15.01.1999 IT MI990073

(71) Applicant: Gigola, Antonio
I-25046 Cazzago San Martino (Brescia) (IT)

(54) Procedure and press for producing screening and humidifying panels, and panels produced by this procedure

(57) A process for manufacturing screening and humidifying panels (10) in particular for air circulation in avicultural facilities or greenhouses comprises the steps of shaping cardboard sheets with non-rectilinear undulated channels (12) by means of sequential pressing of the individual channels (12) and gluing together of the sheets arranged with alternating different mutual incli-

nation of the channels (12). To realize the process a press comprising a die (21) made up of a plurality of segments (24) each representing at least part of a channel (12) and moving sequentially to press the cardboard starting from one end of the press is proposed.




Fig. 1

EP 1 025 985 A1

Description

[0001] The present invention relates to a method for producing screening and humidifying panels in particular for avicultural facilities or greenhouses and a panel produced by this procedure and equipment for this method.

[0002] In the field there are known honeycombed panels with channels extending between the two faces of the panel to allow air passage. There are predominantly two types of panels, to wit screening panels in which the channels are provided so as not to have the two ends aligned and thus prevent or reduce light inlet, and humidifying panels in which are made passages between the channels to permit continuous falling of a water veil to humidify the air passing through the channels.

[0003] Screening panels can be made of any material and in general plastic is preferred so as to press easily the channels with the necessary non-rectilinear configuration.

[0004] Humidifying panels require to be made from moderately absorbent and porous materials to obtain a moist surface as broad as possible in contact with the air. The preferred material is impregnated cardboard which has been found to give the best characteristics in the particular application. Panels are accordingly made from glued cardboard layers appropriately undulated to form air channels and water passages. Unfortunately, by the known techniques it is impossible to make undulated cardboard with non-rectilinear undulations. For this reason the channels of the panels made in this manner are also rectilinear and it is accordingly impossible to make humidifying panels having screening properties also.

[0005] Another problem is that the undulations can be produced continuously only in a direction near the transversal direction of the cardboard strip. This prevents obtaining panels having the inclinations which would be preferable for a more uniform distribution of the water veil. In addition the undulated cardboard layers forming the water passages should have the undulations with extension nearly right above the panel. Such a direction is however also that of maximum transversal extension of the panel. Since the extension of the cardboard in the direction parallel to the undulations coincides with the transversal extension of the cardboard strip during production of the undulations it is difficult and costly to make larger panels.

[0006] The general purpose of the present invention is to remedy the above mentioned shortcomings by making available a production method which would make it possible to obtain cardboard panels with both screening and humidifying functions and in addition with the humidifying function incremented with respect to that of the prior art panels.

[0007] Again in accordance with the purposes of the present invention there is supplied a panel made in

accordance with said method and tools for the method.

[0008] In view of this purpose it was sought to provide in accordance with the present invention a process for manufacturing screening and humidifying panels in particular for avicultural facilities or greenhouses comprising the steps of shaping the cardboard sheets with non-rectilinear undulated channels by means of sequential pressing of the individual channels and gluing together of the sheets arranged with alternating different mutual inclination of the channels.

[0009] Again in view of the above mentioned purposes it is sought to make a screening and humidifying panel in particular for avicultural facilities or greenhouses made up of cardboard sheets shaped by means of pressure with non-rectilinear undulated channels glued together arranged with different mutual alternating inclination of the channels.

[0010] Furthermore it is sought to make a press for obtaining deformed cardboard sheets with channels for manufacturing screening and humidifying panels in particular for avicultural facilities or greenhouses and comprising a bottom die made up of a plurality of segments with each one representing at least part of a channel and movable sequentially for pressing the cardboard starting from one end of the press.

[0011] To clarify the explanation of the innovative principles of the present invention and its advantages compared with the prior art there is described below with the aid of the annexed drawings a possible embodiment thereof by way of non-limiting example applying said principles. In the drawings:

FIG 1 shows a diagrammatic perspective view of a panel in accordance with the present invention, FIG 2 shows a plan view of a layer of the panel, FIG 3 shows a partially cross sectioned side view of the panel, FIG 4 shows a diagrammatic side elevation of a press for obtaining layers in accordance with the present invention, FIGS 5 and 6 shows views similar to FIG 2 but of variant embodiments, and FIG 7 shows a diagrammatic view of a second embodiment of a press in accordance with the present invention.

[0012] With reference to the FIGS a panel 10 is made up of a plurality of layers of sheets 11 of cardboard impregnated e.g. with resin and glued together. Each sheet has shaped on it channels or undulations 12.

[0013] As may be seen in FIG 2 each of the channels 12 has end sections 15 which are near the edges of the sheet which coincide with the two faces 13, 14 for inlet & outlet of air into or from the panel. The sections 15 are basically at a right angle to the sheet edges and are connected by a section of channel 16 inclined so that the mouths of the channels are not in view of each

other along the channel axis. The screening function is obtained in this manner.

[0014] The angle α can be e.g. around 130°. The undulations can have a height of approximately 7mm and the distance d between the crests can be approximately 21mm. As may be seen in FIG 3 neighboring sheets (indicated in the FIG by reference numbers 11a and 11b) are arranged overturned with respect to each other so that the channels on the two sheets have opposing inclinations. The contact points between the channel crests of the two sheets are glued to form the panel.

[0015] In this manner there are obtained channels for conveying the air between the faces 13 and 14 of the panel and the passages 17 which connect the air conveyance channels together and extend between the upper and lower faces 18, 19 of the panel. From the upper face water can thus be inlet to form a veil over all the walls of the sheets. The air humidification function is obtained thus. Thanks to the peculiar form of the channels distribution uniformity and exchange efficiency are much higher than those of conventional panels.

[0016] To be able to deform the cardboard to obtain the channels it has been found necessary to press the undulations on each sheet in sequence starting from one end. This is necessary to allow the cardboard to deform without tearing.

[0017] FIG 4 shows diagrammatically a heated press 20 which obtains that. It comprises a base equipped with a die 21 reproducing the form to be obtained on the cardboard and a segmented moving die 22 with each segment 24 defining a channel. The segments are operated by actuators 23 (only one is shown) to be able to descend on the die 21 in sequence starting from one end to reach the other end of the press. Once all the segments have descended the press can remain closed for the time necessary for permanent deformation of the cardboard.

[0018] FIG 7 shows a possible alternative embodiment of a press in accordance with the present invention. A press 120 comprises a base with a die 121 reproducing the form to be obtained on the cardboard. The upper movable press table 126 supports a segmented movable die 122 in which each segment 114 is connected to the upper table 126 through an elastically yielding member 123, e.g. a spring. The segments 124 are arranged at a growing distance from the table 121 starting from one end and moving towards the other end of the undulated table. In this manner, upon operation of the press the segments 124 close sequentially on the table 121 to deform the cardboard sheet 11. The elastic members are chosen to have sufficient elastic force to produce the correct compression of the cardboard without obstructing press closing. With a single command it is thus possible to obtain sequential deformation of the sheet 11.

[0019] The initial profile of the cardboard sheet to be shaped must allow for the deformation produced by

the press. FIG 2 shows how the sheet should have a lozenge form 25 to become rectangular after forming.

[0020] Surprisingly it has been found that the sequential forming permits deformation in accordance with non-rectilinear undulations without tearing the cardboard.

[0021] It is now clear that the predetermined purposes have been achieved by making available a production method and a panel allowing obtaining both the screening function and the humidifying function.

[0022] Naturally the above description of an embodiment applying the innovative principles of the present invention is given by way of non-limiting example of said principles within the scope of the exclusive right claimed here.



[0023] For example the extension of the panel in all directions and the number of component layers will vary depending on specific requirements. The sheet forming process can also be accomplished by steps with a continuous strip of cardboard extending directly in the direction of greatest contraction caused by the forming as shown in broken lines in FIG 2. The sheets will be trimmed after forming. The configuration of the channels can be different than shown while preserving the screening characteristics. For example FIG 5 shows a panel layer indicated by reference number 111 having channels with initial and final parts 115 inclined in matching manner and the central part 116 at a right angle to the air inlet-outlet edge. FIG 6 shows another embodiment of a layer 211 in which the channels have initial and final parts 215 inclined in opposite direction and the central part 216 at a right angle to the air inlet and outlet edge. Both embodiments can be pressed by the method in accordance with the present invention.

Claims

1. Process for manufacturing screening and humidifying panels and in particular for avicultural facilities or greenhouses comprising the steps of shaping the cardboard sheets with non-rectilinear undulated channels by means of sequential pressing of the individual channels and gluing together of the sheets arranged with alternating different mutual inclination of the channels.
2. Process in accordance with claim 1 characterized in that each channel has end sections near the edges of the sheet which will constitute inlet outlet sides of the panel and which are virtually at a right angle to said edges and inclined sections for connection of said end sections.
3. Process in accordance with claim 1 characterized in that each channel has end sections near the edges of the sheet which will constitute inlet outlet sides of the panel and which are inclined with respect to said edges and sections virtually at a

right angle to said edges for connection of said end sections.

4. Process in accordance with claim 1 characterized in that pressing takes place by means of a plurality of die sections each representing at least part of a channel and moved to press the cardboard sequentially. 5
5. Process in accordance with claim 1 characterized in that the sheets are cut in lozenge shape before pressing to compensate for the contraction produced by the pressing. 10
6. Process in accordance with claim 1 characterized in that the sheets are made from a continuous strip of cardboard extending in the direction of the contraction produced by the pressing and are cut from the strip after pressing. 15
20
7. Screening and humidifying panel in particular for avicultural facilities or greenhouses and formed from cardboard sheets shaped by pressing with non-rectilinear undulated channels and glued together arranged with different mutual alternating inclination of the channels. 25
8. Panel in accordance with claim 7 characterized in that each channel has end sections near the sheet edges which constitute inlet and outlet sides of the panel and which are virtually at a right angle to said edges and inclined sections for connection of said end sections. 30
9. Panel in accordance with claim 7 characterized in that each channel has end sections near the sheet edges which will constitute inlet outlet sides of the panel and which are inclined with respect to said edges and sections virtually at a right angle to said edges and which are for connection of said end sections. 35
40
10. Press for obtaining deformed cardboard sheets for manufacturing screening and humidifying panels in particular for avicultural facilities or greenhouses and comprising a die made up of a plurality of segments each representing at least part of a channel and moving sequentially to press the cardboard starting from one end of the press. 45
50
11. Press in accordance with claim 10 characterized in that the segments of the plurality are supported elastically on a moving press table to press sequentially the cardboard upon operation of the moving press table. 55






Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig.7



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 20 0107

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 4 659 323 A (ITO YUUJI ET AL) 21 April 1987 (1987-04-21) * abstract; claims; figure 6 *	10	B31F1/20
A	-----	1-9,11	
A	US 2 963 128 A (RAPP) 6 December 1960 (1960-12-06) -----		
A	US 5 775 060 A (FERRERO PIETRO) 7 July 1998 (1998-07-07) -----		
A	US 4 512 938 A (KUNESCH ANTHONY M ET AL) 23 April 1985 (1985-04-23) -----		
A	DE 434 650 C (ENDLER) 30 September 1926 (1926-09-30) -----		
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			B31F A01K F24F
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 11 February 2000	Examiner Soederberg, J
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date O : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 20 0107

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file or
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

11-02-2000

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4659323	A	21-04-1987	JP 1034687 B	20-07-1989
			JP 1551481 C	23-03-1990
			JP 60174218 A	07-09-1985
			JP 1022011 B	25-04-1989
			JP 1534271 C	12-12-1989
			JP 60225615 A	09-11-1985
			AU 554689 B	28-08-1986
			AU 3868485 A	12-09-1985
			DE 3505854 A	22-08-1985
			GB 2154154 A,B	04-09-1985
			KR 8901117 B	24-04-1989
			KR 8901118 B	24-04-1989
			PH 23850 A	23-11-1989
			US 4767394 A	30-08-1988

US 2963128	A	06-12-1960	NONE	

US 5775060	A	07-07-1998	CH 681614 A	30-04-1993
			AT 122007 T	15-05-1995
			CA 2110987 A	21-01-1993
			DE 69202339 D	08-06-1995
			DE 69202339 T	28-09-1995
			DK 591300 T	10-07-1995
			WO 9301093 A	21-01-1993
			EP 0591300 A	13-04-1994
			ES 2074366 T	01-09-1995
			JP 6509774 T	02-11-1994
			PL 169983 B	30-09-1996
			PT 100656 A,B	31-05-1994

US 4512938	A	23-04-1985	GB 2101921 A	26-01-1983
			DE 3278441 A	09-06-1988
			EP 0070676 A	26-01-1983

DE 434650	C		NONE	

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office. No. 12/82